



CENTURY COCKLE

description Uncoated woodfree E.C.F. papers and boards, two-sided embossed finish. Available in Premium White, White and Ivory colours. The substance 90 g has a random watermark.

range	size	grain	substance
	45x64	LG	90
	70x100	LG	250

technical features
standard/instrument
unit of measure

substance	VSA	opacity	Taber stiffness 15°		breaking length	
ISO 536	ISO 534	ISO 2471	ISO 2493		ISO 1924	
g/m ²	cm ³ /g	%	mN		m	
			long±10%	cross±10%	long±10%	cross±10%
90 ± 3%	1,24	90 ± 2	5,0	2,4	7400	3700
250 ± 5%	1,24	–	160	71	6000	3000

Whiteness (col. Premium White) - ISO 2470 (R457) - 106% ± 2
Relative Humidity 50% ± 5

watermark



ecological features



ELEMENTAL
CHLORINE
FREE
GUARANTEED



notes

The product is completely biodegradable and recyclable.
Special runs available upon request.



Envelopes available on stock.

The Company reserves the right to modify the technological features of the product in relation to market requirements.



Century Cockle is ideal for writing papers, corporate and social images, monographs, de luxe publications and packaging for cosmetics, jewels, etc.

applications

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing.

printing
suggestions

The macro-porous surface requires the use of oxidative drying inks.

Low substances can also be used with non-impact printing systems: electro-photographic systems, laser and ink-jet printers.

Varnishing and plastic laminating must be assessed in advance. The surface roughness typical of uncoated papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate.

converting
suggestions

Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing.