



STUCCO COROLLA LABEL

description Laid papers made with E.C.F. pulp, with “Stucco” processing on one side. This feature ensures extraordinary printing results. Wet-strength. Available in Premium White and Ivory colours.

range size grain substance
72x101 LG 85

technical features
ref. standard/instrument
unit of measure

| substance | VSA | opacity | cobb 60 | W.B.R. | Dry tensile strength | |
|------------------|--------------------|----------|------------------|----------|----------------------|-----------|
| ISO 536 | ISO 534 | ISO 2471 | ISO 535 | ISO 3781 | ISO 1924 | |
| g/m ² | cm ³ /g | % | g/m ² | % | kN/m | |
| | | | | | long±10% | cross±10% |
| 85 ± 3% | 1,3 | 89 ± 2 | 22 ± 3 | ≥ 13 | 5,2 | 3,2 |

Relative Humidity 50% ± 5 ref. TAPPI 502-98

treatment



ecological features



The mark of responsible forestry

ELEMENTAL
CHLORINE
FREE
GUARANTEED




notes The product is completely biodegradable. Special runs available upon request.

The Company reserves the right to modify the technological features of the product in relation to market requirements.

Stucco Corolla Label has been specially developed for the label sector to exploit the features of laid products together with printing performance of a coated media. For labelling, always observe the correct indications as regards grain direction. It must be parallel to the base of the bottle (see drawings).


applications

Form of the label




wrap-around label

Rolling after wetting the back of the label.



correct grain direction



wrong grain direction

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography, screen printing and bronzing.

In offset printing the macro-porous surface requires the use of oxidative drying inks.

printing
suggestions

Good results with major processing operations such as: cutting, die-cutting and glueing.

converting
suggestions