



OLD MILL

description Uncoated papers and boards, certify FSC, made with E.C.F. pulp. Felt marked on both sides. Substances over 250 g are multi-ply laminated in the formation stage. Available in White and Ivory colours.

range

size	grain	substance					
70x100	LG	100	130	190	250	300	350

technical features
standard/instrument
unit of measure

substance	VSA	Taber stiffness 15°		breaking length	
ISO 536	ISO 534	ISO 2493		ISO 1924	
g/m ²	cm ³ /g	mN		m	
		long±10%	cross±10%	long±10%	cross±10%
100 ± 3%	1,45	10	4	7000	3700
130 ± 3%	1,45	16	7	7400	3600
190 ± 4%	1,45	70	30	5200	2500
250 ± 5%	1,45	185	80	5000	2500
300 ± 5%	1,45	285	130	5500	3000
350 ± 5%	1,45	405	185	5700	3000

Brightness (col. White) - ISO 2470 (R457) - 91% ± 2
Relative Humidity 50% ± 5

ecological features



notes The product is completely biodegradable and recyclable. Special runs available upon request.

The Company reserves the right to modify the technological features of the product in relation to market requirements.



Old Mill is a high-quality finely felt marked paper for de luxe publications and editions, important commercial printing as well as institutional brochures, annual reports, monographs.

applications

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks. The chromatic and tone performance is good, the ink load, the dot gain, and the print contrast are at the best levels attainable from uncoated paper.

printing
suggestions

Varnishing and plastic laminating must be assessed in advance. The varnishing coated with an offset machine is almost fully absorbed and therefore does not improve gloss or protection. Screen-printing varnishing achieves better results, although it is often necessary to perform two shots to achieve a distinctly evident result. The surface roughness typical of felt marked papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate. Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing.

converting
suggestions